

## Santa Cruz

Nm. 2/28

100% Llama Soft

Macchina rettilinea: 1 filo finezza 12

Flat knitting machine: 1 ply 12 gauge

## La Paz

Nm. 2/32

70% Llama Soft

30% Mulberry Silk

Macchina rettilinea: 1 filo finezza 12-14

Flat knitting machine: 1 ply 12-14 gauge

## Phuio

Nm. 3000

75% Llama Soft

25% Polyamide

Macchina rettilinea: 1 filo finezza 3-5

Flat knitting machine: 1 ply 3-5 gauge

### Finishing | Finissaggio

Wash in 50 litres of water by 1 kg of material for 3 minutes at 20° water. 5 gr/lt of syliconic softener. 1 gr/lt of acetic acid. Tumbler dry at 60° for 25 minutes. Ironing with steam iron.

Lavare in 50 litri d'acqua per 1 chilo di materiale per 3 minuti in acqua a 20°. 5 grammi per litro di ammorbidente siliconico. 1 grammo per litro di acido acetico. Asciugare in tumbler a 60° per 25 minuti. Stiro con ferro a vapore

### Use for stripes / intarsio | Utilizzo per rigature / jacquard

Melange colours: YES Solid colours: ASK FOR | Colori melange: SI Colori uniti: CHIEDERE SPECIFICHE

### Minimums | Minimi

Stock colours: 1 Kg | Colori in stock service: 1 Kg

### Optimal dye-lots | Cotte ottimali

Solid colours | Colori uniti: 4-9-13-27-63-102-126-252-264-504

Dry clean only



Associazione Tessile e Salute

This item meets all the requirements of the

**HEALTH AND TEXTILE PROJECT**

promoted by the

ITALIAN MINISTRY OF HEALTH

certificate no. **14900136**

